

TECHNICAL INFORMATION



RIGENERATO HAX NERO

January 2009

THERMOPLASTIC HALOGEN FREE, FLAME RETARDANT AND LOW SMOKE EMISSION COMPOUND, FOR CABLE APPLICATIONS

Description

Rigenerato HAX nero is a thermoplastic flame retardant black coloured compound, and halogen free on polyolefinic basis. It can be used for the production of energy, signal and control cables.

Technical characteristics:

Property	Test method	Unit	Typical Value
Density	ISO R 1183	gr/cc	1.50 ± 0.1
Hardness at 15"	ISO R 868	Shore D	50 ± 5
Tensile strength	ISO R 527	N/mm ²	≥ 10
Elongation at break	ISO R 527	%	≥ 120
Oxygen Index	ISO 4589	% O ₂	38 ± 5
Melt Flow Index (21.6Kg AT 150°C)	ISO 1133	gr/10 min	6 ± 3
HCl & HBr gas evolution	EN 50267-2-1	%	< 0.5
Volume Resistivity 20°C (Alternating Polarity Method)	ASTM D257 Electrodes	Ωcm	> 10 ¹⁴

The typical values reported in the table have been obtained from measurements made on extruded samples or pressed plates

The description and figures contained herein are provided to customers as a general information for the purposes the product is intended for. These reflect FAINPLAST knowledge at the time of publication. By the information contained herein FAINPLAST won't release any warranty and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. This document does not form part of any contract with customer.

Processing

This thermoplastic compound has been designed for an easy processing, whilst maintaining good mechanical-thermal properties, and a medium-high LOI value.

It can be processed using extruders with a low screw compression ratio (halogen free or PVC type), and with a temperature profile as that given below, which is however indicative, as it may depend on the equipment design adopted.

Zone 1	Zone 2	Zone 3	Zone 4	Collar	Head	Die
130 - 150	130 - 160	140 - 160	140 - 160	150 - 165	150 - 165	150 - 170

Storage

The thermoplastic compound must be stored at ambient temperature (not exceeding 30°C) in closed and unbroken bags, in order to avoid exposure to sunlight and water absorption. Long stocking time may negatively affect the quality of the material. Therefore it is preferable to use it within 6 months from the compounding date.

Packaging

Rigenerato HAX nero is available in 25 Kg PE bags, big bags or octabins of 1250 Kg. Our technical service is at your disposal, for further information and assistance.

www.fainplast.com

info@fainplast.com

The description and figures contained herein are provided to customers as a general information for the purposes the product is intended for. These reflect FAINPLAST knowledge at the time of publication. By the information contained herein FAINPLAST won't release any warranty and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. This document does not form part of any contract with customer.
