



Grade	Description	Density	Hardness At 15"	Tensile Strenght	Elongation at Break	M.F.I. 2,16 Kg-230°C	Volume Resistivity at 20°C	Dielectric constant
		ISO 1183 gr/cm <sup>3</sup> (±0,02)	ISO 868 Shore D (±3)	ISO 527 MPa	ISO 527 %	ISO 1133 gr/10'	ASTM D257 Ωcm	(1Mhz)
700	High temperatures; signal and control cables	0,9	61	28	750	4	> 1x10 <sup>17</sup>	2,28
703	High temperatures; signal and control cables	0,89	49	25	700	1,7	> 1x10 <sup>16</sup>	
705	High temperatures; signal and control cables	0,87	39	22	700	0,5	> 1x10 <sup>16</sup>	