

ITCOGEL T 300 R

ITCOGEL T 300 R Tube Filling Compound (Thixotropic Jelly) is a soft, non-melting, translucent, water barrier compound. It is based on synthetic and aliphatic hydrocarbons and has been formulated to meet a wide range of processing and performance requirements. It has been designed Optical Fibre Cables with ribbon designs (ribbons in loose tube & slotted core).

ITCOGEL T 300 R remains sufficiently flexible until – 50°C and exhibits good stability even at + 85°C.

Appearance	Translucent Gel without visible impurities	Visual (Erichsen Gauge 100 µ)
Flash Point COC - °C	> 230	ASTM D 92
Drop Point - °C	> 200	ASTM D 566
Viscosity at 25°C, 100 rpm - cps	25000 ± 5000	Brookfield Viscometer HADV, Spindle No. 7
Viscosity (Typical) at 25°C, D = 50 1/S - mPas	9600	Haake Rheometer RV1 (DIN 53019)
Cone Penetration - 1/10 mm at + 25°C at - 40°C Typical Values : + 25°C - 40°C	≥ 350 > 230 370 250	ASTM D 937
Density at 25°C - g/cm ³	0.84 ± 0.01	ASTM D 1217
Volatility, 24 hrs at 150°C - %	< 1	FTM 791 C
Oil Separation, 24 hrs at 150°C - %	Zero	FTM 791 C
Oxidation Induction Time, 190°C, Alu. Pan – minutes	> 30	ASTM D 3895
Tube Drainage in 2.0 mm ID Empty Tube, 24 hrs at 80°C	Pass	ITCO : ITM 09
Hydrogen Generation, 24 hrs at 80°C - µl/g	< 0.03	ITCO : ITM 28

Packing In metal drums with epoxy lining : Height – 885 mm, Internal Diameter – 570 mm, 170 Kg Nett weight.
Bulk Bag (Fluid Bag) with 700 / 750 Kg Nett weight.

Storage Minimum 3 years in original packed condition stored at room temperature.

Safety As per our knowledge and available information, ITCOGEL T 300 R does not pose any health hazard. For further information, please refer to MSDS a copy of which is available upon request.

Compatibility ITCOGEL T series products have been tested and found compatible with most of the associated cable materials including Fibre Coatings and Colouring Inks. Further information is available upon request.

Itco Industries Limited

321, Raheja Arcade, Koramangala, Bangalore 560 095 India

Information provided in this Data Sheet is based on our knowledge and experience and is meant for general guidance only, without guarantee or representation as to results. Suitability of the product for an intended use shall be the sole responsibility of the user. We reserve the right to modify the above specified values without notice. For further information regarding material specification and / or application conditions, please contact ITCO Industries Limited.

ITCOGEL™