

TECHNICAL INFORMATION



PROPYLPLUS 700

October 2015

THERMOPLASTIC POLYPROPYLENE COMPOUND FOR WIRE AND CABLE INSULATION

Description

Propylplus 700 is a polypropylene and halogen free compound specially designed for those applications requiring superior thermo-mechanical properties, outstanding heat resistance and electrical properties with the presence of a mix of antioxidants and a metal deactivator. It can be used as primary insulation on computer, telephone and instrument wires. The properties of this compound comply with the requirements of VDE 0250, Part 215, type 9YI2 and CEI-EN 60811-4-2.

Technical characteristics

Property	Test method	Unit	Typical Value
Density	ISO 1183	g/cm ³	0.90
Hardness at 15"	ISO 868	Shore D	61
Tensile strength (v = 50 mm/min)	ISO 527	N/mm ²	28.0
Elongation at break (v = 50 mm/min)	ISO 527	%	750
Pressure test at 120 °C	IEC 60811	%	< 50
Melt Flow Index (230 °C / 2.16 Kg)	ISO 1133	g/10 min	4.0
Volume Resistivity 20 °C (Alternating Polarity Method)	ASTM D257 Electrodes	Ω·cm	> 1 · 10 ¹⁷
Dielectric Constant (1 MHz)			2.28

The typical values reported in the table have been obtained from measurements made on extruded samples or pressed plates

Processing

This thermoplastic compound has been formulated for an easy processing, and optimal output can be generally achieved on extruders with $L \geq 20D$ using a temperature profile between 180°C and 240°C.

Packaging

Available in 20 Kg PE bags, big bags or oktabinos of 1000 Kg.

Our technical service is at your disposal, for further information and assistance.

Faraotti Industrie Plastiche Srl
Zona Ind.le Campolungo II fase
63100 Ascoli Piceno (AP) – Italia
tel +39 0736 403605, fax +39 0736 403807
info@fainplast.com, www.fainplast.com



The description and figures contained herein are provided to customers as a general information for the purposes the product is intended for. These reflect FAINPLAST knowledge at the time of publication. By the information contained herein FAINPLAST won't release any warranty and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. This document does not form part of any contract with customer.