



Crosslinkable Semi Conductive Compound For CCV :

**KI – XLC – 09S**

## **CROSSLINKABLE SEMICONDUCTIVE STRIPABLE INSULATION SHIELDING COMPOUND FOR POWER CABLE**

### **DESCRIPTION :**

KI-XLC-09S is a specially formulated, cross-linkable polyethylene copolymer semiconductive compound for strippable insulation shielding of medium voltage XLPE power cables. It is suitable for both tandem and triple common head extrusion process in steam or dry curing system.

### **SPECIFICATIONS :**

Cables with strippable insulation, shielding of KI-XLC-09S when made using standard manufacturing and test procedure meet the following cable specifications:

- IEC – 60502
- NEMA – WC – 7
- AEIC – CS – 5 / AEIC – CS5
- IS – 7098 – II

### **TYPICAL PROPERTIES :**

<b>Property</b>	<b>Unit</b>	<b>Typical Value</b>	<b>Test Method</b>
Density	gm / cm <sup>3</sup>	1.17	ASTM-D-792
Tensile Strength	MPa	14	ASTM D-638
Variation in Tensile Strength*	%	< 20	IEC-60811-1-2 cl-9
Elongation at break	%	> 250	ASTM-D-638
Variation in elongation at break*	%	< 20	IEC-60811-1-2 cl-9
Hot elongation @200°C, 20N/cm <sup>2</sup>	%	45	IEC-60811-1-2 cl-9
Shore D Hardness	-	50	ASTM-D-2240
Moisture Content	ppm	< 300	Karl Fischer
DC Volume Resistivity @ 25°C	Ohm-cm	< 50	ASTM-D-991
DC Volume Resistivity @ 90°C	Ohm-cm	< 500	ASTM-D-991
Stripping Force	Kg/12.7 mm	3.0 – 5.00	ASTM-D-903

*MKT: TDS – XLC/09S – 03/14*



# Kalpena Industries Limited

- \* After Heat ageing at 135°C for 168 hours.
- \* On moulded sheet at 180°C / 20 min.

Specific processing conditions depends on type / size of the extruder and cable dimension and output.

## RECOMMENDED PROCESSING CONDITIONS :

Position	Temperature (°C)
Barrel	85 - 105
Head	110
Die	110

**PACKAGE** : 500 & 650 kgs Corrugated Paper Boxes with PE liner, other packings to Customer's Specific requirements are also available.

**STORAGE** : Storage should be in cool and dry place. Boxes should be kept on Wooden or plastic pellets.

---

*The information given in the document is believed to be reliable and is given in the good faith but without warranty. The user should test the product to ascertain the suitability for the intended use. Product specification or the whole document is subject to change without any prior notice.*

**MKT: TDS – XLC/09S – 03/14**